



Technical Data Sheet

Product Number: PVL20240

Product Name: VALLEY GREEN 21219 (3879130) POL.

Chemistry: POLYESTER TGIC

Date: MARCH 30TH, 2011

Powder Properties

| | | |
|------------------------|----------------------|---|
| ASTM D5965 (B) | Specific Gravity | 1.50 ± 0.05 |
| PCI TECHNICAL BRIEF #8 | Theoretical Coverage | 128.1 ft ² /lb/mil |
| | Shelf Life | 12 months in climate controlled environment |

Film Characteristics

| | | |
|-------------------------|--------------------------------|----------------|
| ASTM D523 | Gloss @ 60° | 85-95% |
| ASTM D3359 (B) | Adhesion | 5B Pass |
| ASTM D3363 | Pencil Test (Scratch Hardness) | 2H Pass |
| ASTM D7091 | Recommended Film Thickness | 2.0-3.0 mils |
| PCI TECHNICAL BRIEF #20 | PCI Powder Smoothness | 5 |
| ASTM D522 (A) | Flexibility Mandrel | 1/8" |
| ASTM D2794 | Indirect Impact | 160 in/lbs |
| ASTM D5402 | MEK Resistance | 25 Double Rubs |
| ASTM B117 | Salt Spray | 1,000 hours |
| ASTM G154 | UV Resistance | 500 hours |

Application

Electrostatic Spray, Cold
Substrate: 0.024 in. CRS
Pretreatment: Bonderite® 1000 , Parcolene® 60

Cure Schedule
(Time at Substrate Temperature)
375 °F @ 7 minutes

Notes

American Standard Testing Method (ASTM)
Powder Coating Institute

This report cannot be altered or changed without the authorization of the Quality Manager.

Vitracoat, Inc.

2807 Marina Drive Elkhart, IN 46514 Ph: 574-264-6090
Toll-Free: 888-778-5994 Fax: 574-264-2776 www.vitracoat.com

Vitracoat Pinturas en Polvo S.A de C.V.

Av. Circuito de la Industria Sur 284, Parque Industrial Lerma, C.P. 52000, Estado de Mexico, México, Phone: +(722) 2627000, Fax+(722)2827024
www.vitracoat.com*Email:sales@vitracoat.com