



Technical Data Sheet

Product Number: HSM50238

Product Name: SILVER VEIN

Chemistry: Hybrid

Date: January 19, 1998

Powder Properties

ASTM D5965 (B)	Specific Gravity	1.20± 0.05
PCI TECHNICAL BRIEF #8	Theoretical Coverage	160.2 ft ² /lb/mil
	Shelf Life	12 months in climate controlled environment

Film Characteristics

ASTM D523	Gloss @ 60°	20-50
ASTM D3359 (B)	Adhesion	5B Pass
ASTM D3363	Pencil Test (Scratch Hardness)	3H Pass
ASTM D7091	Recommended Film Thickness	3.5-5.0 mils
PCI TECHNICAL BRIEF #20	PCI Powder Smoothness	N.A.
ASTM D522 (A)	Flexibility Mandrel	1/8" Pass
ASTM D2794	Impact (D/R)	140/140 in-lbs
ASTM D5402	MEK Resistance	25 Double Rubs
ASTM B117	Salt Spray	N.A.

Application

Electrostatic Spray, Cold
Substrate: 0.024 in. CRS
Pretreatment: Bonderite® 1000, Parcolene® 60

Cure Schedule
(Time at Substrate Temperature)
15 min @ 356°F

Notes

This product was designed for interior use only.

American Standard Testing Method (ASTM)
Powder Coating Institute (PCI)

This report cannot be altered or changed without the authorization of the Quality Manager.

Vitracoat, Inc.

2807 Marina Drive Elkhart, IN 46514 Ph: 574-264-6090
Toll-Free: 888-778-5994 Fax: 574-264-2776 www.vitracoat.com

Vitracoat Pinturas en Polvo S.A de C.V.

Av. Circuito de la Industria Sur 284, Parque Industrial Lerma, C.P. 52000, Estado de Mexico, México, Phone: +(722) 2627000, Fax+(722)2827024
www.vitracoat.com*Email:sales@vitracoat.com