



Technical Data Sheet

Product Number: PZL20836

Product Name: BLUE STREAK III 22673 (7PPTSTRKBLU) POL.

Chemistry: POLYESTER TGIC

Date: OCTOBER 07TH, 2011

Powder Properties

ASTM D5965 (B)	Specific Gravity	1.70 ± 0.05
ASTM D5965 (B)	Theoretical Coverage	113.1 ft ² /lb/mil
	Shelf Life	12 months in climate controlled environment

Film Characteristics

ASTM D523	Gloss @ 60°	80-90%
ASTM D3359 (B)	Adhesion	5B Pass
ASTM D3363	Pencil Test (Scratch Hardness)	F Pass
ASTM D1186 (B)	Recommended Film Thickness	2.0-3.0 mils
DPC TM 10.219	PCI Powder Smoothness	4
ASTM D522 (A)	Flexibility Mandrel	1/8"
ASTM D2794	Indirect Impact	80 in/lbs
ASTM D5402	MEK Resistance	25 Double Rubs
ASTM B117	Salt Spray	1,000 hours
ASTM G154	UV Resistance	500 hours

Application

Electrostatic Spray, Cold
Substrate: 0.024 in. CRS
Pretreatment: Bonderite® 1000 , Parcolene® 60

Cure Schedule
(Time at Substrate Temperature)
356 °F @ 15 minutes

Notes

We guarantee that the above referenced product when properly applied and cured, complies with the U.S. Consumer Product Safety Commission

(I) 16 CFR Part 1303, Ban of Lead-Containing Paint and Certain Consumer Products Bearing Lead-Containing Paint

(II) Section 14(g) of the consumer Product Safety Act 15 USC 2063 (g) for Section 101, Lead and/or Section 108, Phthalates of the Children's Product Safety Rule as specified in Consumer Product Safety Improvement Act (CPSIA) of 2008 (H.R. 4040), Public Law No. 110-314

American Standard Testing Method (ASTM)
Powder Coating Institute

This report cannot be altered or changed without the authorization of the Quality Manager.

Vitracoat, Inc.

2807 Marina Drive Elkhart, IN 46514 Ph: 574-264-6090
Toll-Free: 888-778-5994 Fax: 574-264-2776 www.vitracoat.com

Vitracoat Pinturas en Polvo S.A de C.V.

Av. Circuito de la Industria Sur 284, Parque Industrial Lerma, C.P. 52000, Estado de Mexico, México, Phone: +(722) 2627000, Fax+(722)2827024
www.vitracoat.com*Email:sales@vitracoat.com